

PLA SATIN

PLA SATIN is a PLA based material developed for its silky and smooth shine. It increases the perception of colour brilliance and disperses light when viewed from different angles giving a unique glossy effect. Slower printing and low temperature improve the silky effect. The satin surface creates beautiful reflection in printed objects.

Material features:

- High light reflection
- Smooth and silky
- Fantastic Satin look
- Deep colours



Colours:

PLA SATIN is available from stock in 9 colours.



Packaging:

PLA SATIN is available in nearly any type of packaging and labelling. Ask our team to help you customizing your product.

Filament specs.

Size	Ø tolerance	Roundness
1,75mm	± 0,05mm	≥ 95%
2,85mm	± 0,10mm	≥ 95%

Material properties

Description	Testmethod	Typical value
Specific gravity	ISO 1183	1,24 g/cc
MFR 210°C/2,16 kg	ISO 1133	8,2 g/10 min
Tensile strength at yield	ISO 527	71 MPa
Tensile strength at break	ISO 527	71 MPa
Elongation strain at yield	ISO 527	3,2%
Elongation strain at break	ISO 527	3,6%
Tensile (E) Modulus	ISO 527	3200 MPa
Impact strength charpy method 23°C	ISO 179 1eA	2,6 kJ/m2
Vicat softening temp.	ISO 306 B50	58,2°C
Printing temp.	Internal Method	225±10°C

Additional info:

Due to its low tendency to warp PLA SATIN can also be printed without a heated bed. If you have a heated bed the recommended temperature is ± 50-60°C. PLA SATIN can be used on all common desktop FDM or FFF technology 3D printers.

Storage: Cool and dry (15-25°C) and away from UV light. This enhances the shelf life significantly. *Please note: the parameters you use for printing with PLA SATIN can change the PLA SATIN effect on printed parts. Looking into the parameters and fine-tune the profile for your printer will benefit the Satin effect of your printed part.*

"The values presented in this publication are based on MCPP's knowledge and experience and are intended for reference purposes only. While MCPP has made every reasonable effort to ensure the accuracy of the information in this publication, MCPP does not guarantee that it is error-free, nor does MCPP make any other representation, warranty or guarantee that the information is accurate, correct, reliable or current. MCPP reserves the right to make any adjustments to the information contained herein at any time without notice. MCPP expressly disclaims warranties of any kind regarding the information contained herein, including, but not limited to, any warranties of merchantability or fitness of a particular purpose, use or application. MCPP shall not be liable for any damage, injury or loss induced from the use of MCPP's products in any application. Each user should thoroughly review this publication before selecting a product and, in view of the many factors that may affect processing and application of the product, each user should carry out their own investigations and tests and determining the safety, lawfulness, technical suitability, proprietary rights, and disposal/ recycling practices of the materials for the intended application."